

ACRYLI-QUIK™

Krylon[®] Industrial Acryli-Quik[™] is specifically formulated for industrial maintenance and touch-up applications. Performance is exceptional, and the broad selection includes interior/exterior acrylic lacquers, primers and specialty paints. Acryli-Quik[™] provides a high-solids, fast-drying formula. No Runs, No Drips, No Errors![™]

- No recoat window, recoat anytime \checkmark
- Dries to a touch in 12 minutes
- Hard, protective, durable finish
- **High-Gloss finish**

INDUSTRIAL USE ONLY!

krylonindustrial.com 1-800-247-3266

RECOMMENDED USES

- Metal
 - Wood
 - Pipelines Motors
 - Conduit

Tools

Drums

Ducts

- Cabinets
- Furniture Color coding steel
 - and lumber

SURFACE PREPARATION

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. For more information, contact your local health authority. Remove dirt, grease, wax, moisture, rust and loose paint from surface. Scuff-sand rusted, glossy or hard surfaces. Sand metal, wood or plastic with #220 grit sandpaper. Use a primer on new wood and on new or rusted metal to smooth uneven surfaces, or when dramatically changing color. For best results, use with Krylon Industrial White (K01315), Gray (K01318) or Ruddy Brown (K01317) Primers. Allow primer to dry for at least 30 minutes before lightly sanding and top coating with Krylon Industrial Acryli-Quik[™] paints.

CLEAN-UP

Use lacquer thinner to remove. Clean spray valve immediately after use by turning can upside-down and spraying until only clear gas comes out. Dispose of in accordance with local, state or federal regulations.

TECHNICAL DATA	
Vehicle	Acrylic Lacquer
Finish	Flat (Primer), High (Gloss)
Flash Point	-20°
Weight/Gallon	6.07 lb/gal
VOC/MIR	1.29
Spread Rate	15-20 sq. feet
Shelf Life	60 months
Drying Time	To Touch: 12 minutes
	To Recoat: Anytime
	To Handle: 30 minutes
Dry Heat Resistance	<150°
Gas Resistance	Film Softens after 15 mins
Oil Resistance	Film Softens after 15 mins
Clean Up	Lacquer Thinner
Net Weight/Can Size	12 oz. / 16 oz.

APPLICATION

APPLICATION CONDITIONS

Use at 70°F for best operation. Shake can until ball rattles for 1 minute. Test spray on inconspicuous area or scrap piece to check compatibility. Hold container upright 10-12 inches from surface. Do not apply with a continuous spray. To avoid runs apply several thin coats. Dries to touch in 12 minutes. Can be recoated at anytime.

CAUTIONS

FOR INDUSTRIAL USE ONLY. Thoroughly review product label and SDS for safety and cautions prior to using this product. Please direct any questions or comments to your local Krylon Industrial Representative.

Note: The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, Krylon Products Group cannot make any warranties as to the end result. Please direct any questions or comments to 1-800-247-3266.

The information and recommendations set forth in the Product Data Sheet are based upon tests conducted by or on behalf of Krylon® Industrial. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Krylon® Industrial dealer or representative to obtain the most recent Product Data Sheet.